

LED热沉基板企业标准-RMT20120315-2

Standard of Heat sink wafer for LED-RMT20120315-2

上海瑞铂特金属新材料有限公司 Shanghai Rare Metal Advanced Materials Co.,Ltd

Item	2 inch	4 inch	5 inch	6 inch
直径 Diameter (mm)	50.8 mm 2 inch	101.6 mm 4 inch	127 mm 5 inch	152.4 mm 6 inch
厚度 Thickness (μm)	100~200±10	100~200 ± 10	100~200 ± 10	100~200 ± 10
材质 Composition	W: 85±1 wt%; Cu: balance			
供货状态 Delivery State	退火态; Annealed			
表面状态 Surface State	轧制表面, 类镜面, 磨光表面, 电镀表面, (按照客户要求). Rolled surface, like mirror surface, grinding surface, plating surface. (according to the buyer's required)			
表面粗糙度 Surface roughness, Ra (μm)	0.04~0.1			
平面度 Flatness (μm)	20~50	50~80	80~100	100~150
TTV Total Thickness Variation(μm)	2~15			
密度 Density (g/cm ³)	16.25~16.50			
相对密度 Relative Density %TD	>99%			
热膨胀系数 Coefficient of Thermal Expansion(10 ⁻⁶ /K)	5.4~5.8			
热导率 Thermal Conductivity (W/mK)	180~200			
比热容 Specific Heat Capacity (J/kgK)	175			
维氏硬度 Vickers Hardness (HV10)	230~350			

本标准负责起草单位: 上海瑞铂特金属新材料有限公司

This standard is issued by: Shanghai Rare Metal Advanced Materials Co., Ltd

本标准主要起草人: 罗建军博士; 时晓明

Major drafter: Dr. Jianjun Luo; David Shi

This standard is copyrighted by Shanghai Rare Metal Advanced Materials Co., Ltd, No.88 Shangtong Road, Shanghai, China. Individual reprints (single or multiple copies) of this standard may be obtained by contacting Shanghai Rare Metal Advanced Materials Co., Ltd at the above address or at +86-21-67291503 (phone), +86-21-67291466(fax), or info@sh-raremetal.com (email)